K&K
Elastomere
GmbH

Rubber • Compounds • Tyres

Dorfstrasse 18

D-22955 Hoisdorf

Tel. 0049 4107 33 00 62/61

E-Mail: kk@info-elastomere-gmbh.de

TYP	KK-70/25	KK-75/25	KK-75/30	KK-80/30	KK-80/50	KK-38/HFFR
application	Cable filler for PVC-insulated cables	Cable filler for PVC-insulated cables	Cable filler for XLPE-insulated cables	Cable filler for XLPE-insulated cables	Cable filler for XLPE-insulated cables	Cable filler for PVC-insulated cables
base polymer	EP(D)M	EP(D)M	EP(D)M	EP(D)M/IIR	EP(D)M	TPE-O
Color	natural	natural	natural	natural	natural	natural
Shape	Granules 3x7 mm	Granules 3x7 mm	Granules 3x7 mm	Granules 3x7 mm	Granules 3x7 mm	Granules 3x7 mm
specific gravity	1,91+/-0,03 g/cm3	1,95+/-0,03 g/cm3	1,85+/-0,03 g/cm3	1,90+/-0,03 g/cm3	1,73+/-0,03 g/cm3	1,88+/-0,03 g/cm3
hardness	70 +/- 5°ShA	80 +/- 5°ShA	75 +/- 5°ShA	75 +/- 5°ShA	75 +/- 5°ShA	70 +/- 5°ShA
viscosity	23 +/- 5ML{1+4}100°C	28 +/- 5ML{1+4}100°C	35 +/- 5ML{1+4}100°C	30+/- 5ML{1+4}100°C	45 +/- 5ML{1+4}100°C	25 +/- 5ML{1+4}100°C
oxygen index	-	-	-	-	-	≥38 % 02
halogen content	Halogen free	Halogen free	Halogen free	Halogen free	Halogen free	Halogen free
packaging	1.250 kg	1.250 kg	1.250 kg	1.250 kg	1.250 kg	1.250 kg